

RHEOBUILD[®] LD80

High range water reducing / superplasticising concrete admixture

Description

RHEOBUILD[®] LD80 is a high range, high performance superplasticiser and water reducing agent specifically designed for the production of rheoplastic concrete required for piling etc. RHEOBUILD[®] LD80 disperses and deflocculates cement particles thereby increasing the workability and flowability of the concrete mixes.

Primary uses

- For all piling applications including C.F.A.
- For the production of flowing concrete.
- To increase workability.
- For hot weather concreting.
- For controlled delays to initial and final setting of concrete mixes.

Typical applications

RHEOBUILD[®] LD80 is recommended for use wherever the following situations are encountered:

- For piling concrete.
- Concrete containing pozzolanic materials.
- In areas of congested reinforcement where high workability and cohesion are of benefit.

Composition

A multi-component admixture based upon high molecular weight polymers and refined lignosulphonates.

Advantages

- Effective over high range of cement contents and types.
- Improves pumpability, durability and impermeability.
- Extended slump retention time - maintains workability in excess of concrete produced utilising conventional superplasticisers

- Reduces placing problems in hot weather by improved workability retention in conjunction with controlled setting times.

Action

RHEOBUILD[®] LD80 acts on the cement particles by its powerful deflocculating and sequestering action to retard and maximise the hydration of the cement paste. Its powerful plasticising action results in high workability concrete which is responsive and cohesive. This action enables concrete with low or reduced water contents to be produced.

Packaging

RHEOBUILD[®] LD80 is available in bulk or in 210 litre drums.

Typical properties

Properties listed are only for guidance and are not a guarantee of performance

Colour:	dark brown liquid
Specific gravity:	1.195 at 25°C
Chloride content:	Nil to BS 5075 Part 1
Nitrate content:	Nil
Freezing point:	0°C
Flashpoint:	N/A

Standards

ASTM C-494 Types D and G

BS 5075 : Part 1. Retarding / Superplasticising

RHEOBUILD[®] LD80

Directions for use

RHEOBUILD[®] LD80 should be added to the concrete mix during the mixing cycle at the same time as the water. Never add RHEOBUILD[®] LD80 to the dry cement. Alternatively when using RHEOBUILD[®] LD80 to produce flowing concrete at site using transit mixer trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Ensure at least 5 minutes mixing before discharge - minimum drum revolution of 10 rpm - to produce a fully homogenous mix.

Dosage

Field trials should be conducted to determine the optimum addition rates of RHEOBUILD[®] LD80. The following figures should be utilised as a starting point for these trials.

Flowing concrete:

An addition rate of 600 to 800ml per 100kg cement is usually required to produce flowing concrete from a concrete with an initial slump in the range of 50-70mm.

High strength, high workability concrete:

Using RHEOBUILD[®] LD80 at 750 - 1000ml per 100kg, concrete mixes can be produced with a reduction in water in the region of 10 to 15% and an increase in workability of between 100 to 150%.

Compatibility

RHEOBUILD[®] LD80 can be used with all types of Portland cement including Sulphate Resisting and modified cement (Type II). For use with special cements, contact BASF's Technical Services Department.

RHEOBUILD[®] LD80 should not be premixed with other admixtures. If other admixtures are to be used in the concrete containing RHEOBUILD[®] LD80, they must be dispensed separately. Contact BASF's Technical Services Department for further advice.

Effects of over dosage

A severe over dosage of RHEOBUILD[®] LD80 will result in the following:

- Retardation of initial and final set.
- Increase in air entrainment.
- Increase in workability.

Providing it is properly cured, the ultimate strength of the concrete will not be adversely affected and will generally be higher than for normal concrete. The effect of over dosage will be exaggerated with SRC cement.

Dispensing

RHEOBUILD[®] LD80 should be dispensed through a proprietary dispenser, such as is available from BASF. Details available upon request.

Safety precautions

RHEOBUILD[®] LD80 contains no hazardous substances requiring labelling. For further information, refer to material safety data sheet.



The Chemical Company

RHEOBUILD[®] LD80

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is up to 2 years when stored as above. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

03/94 BASF_CC-UAE revised 05/2006

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800

www.basf-cc.ae

Fax: +971 4 8851002

e-mail: marketingcc.mideast@basf.com



Certificate No.
963680



Certificate No.
945787



Certificate No.
772556